



SISSONS PAINTS (THAILAND) LTD.

บริษัท ซีสชั่นส์เพ้นท์ส (ประเทศไทย) จำกัด

ได้รับการรับรองระบบคุณภาพมาตรฐาน ISO 9001 จาก SGS (Thailand) Limited.



91/2 หมู่ 3 ถนนสุวินทวงศ์ มีนบุรี กรุงเทพฯ 10510 โทร +66 (0) 2517 1146, 2918 6760 โทรสาร +66 (0) 2517 2137

SISCOGUARD FINISH 100

EPOXY COATING, SOLID 100%

PRODUCT DESCRIPTION	A two component, 100% solid epoxy coating formulated to provide an attractive high gloss and durable finish. It is a quite smooth protective finish coat suitable for coat on most substrates.					
SPECIFIC PROPERTIES	High gloss finish Excellent mechanical and chemical resistance Easy to clean and maintenance Suitable for applied at 200-600 microns DFT. Solvent free – no aids ventilation required during application					
PHYSICAL DATA	Solids (% by volume)	..100...%				
	Dry Film Thickness	200-600 micron				
	Wet Film Thickness	200-600 micron				
	Flash Point	> 90 °C				
	Theoretical Coverage	1.4-1.5 kg/m ² /1000 microns				
	Colours	Various				
	Gloss	Gloss				
APPLICATION DATA	Application method	Roller, paint, trowel				
	Temperature minimum	5 °C				
	Humidity Maximum	85% R.H.				
	Mixing Ratio	4 Base : 1 Hardener (by weight)				
	Drying Time					
	Surface Temperature	Touch Dry	Hard Dry	Over coating Interval		Pot Life
				Minimum	Maximum	
	25 °C	6 Hrs	24 Hrs	24 Hrs	--	1 Hrs
	30 °C	5 Hrs	16 Hrs	16 Hrs	--	50 Mins
	35 °C	4 Hrs	12 Hrs	12 Hrs	--	40 Mins
ADDITIONAL INFORMATION	Resistance to the following substances is extremely good, but in all cases of chemical spillage it is essential that the chemicals be removed as quickly as possible and the surface washed down with water. 10% Hydrochloric, 5% Nitric, 5% Phosphoric, 10% Sulfuric, 28% Ammonium hydroxide, 10% Potassium hydroxide, 10% Sodium hydroxide, 6% Sodium hyperchlorite, Bancker C, Diesel Fuel, Isopropanol, Kerosene, Naphtha, Salt water, Sweage, Xylene, Toluene, Aluminium Chloride(Dry), Tar, Starch, Sodium silicate, Lead Acetate, Magnesium bisulfate, magnesium chloride, Ethylene Glycol, ferrous sulfate, Zinc Sulfate etc. Cleaning Solvent Thinner No.9 Packaging Two pack product, 20 kg/set Preferable Preceding Coats Siscofloor 105 Preferable Subsequent Coats -					
SAFETY PRECAUTIONS	Ensure that there is adequate ventilation in the area where the product is being applied. Do not breath vapour or spray. In case of touch skin, wash skin thoroughly soap and water. In case of accidental eyes splashes, flush eyes with warm water immediately and obtain medical advice.					
DISCLAIMER	The information in this data sheet is given to the best of our knowledge based on laboratory testing and practical experience. However, as the product is often used under conditions beyond our control, we cannot guarantee anything but the quality of the product itself. We reserve the right to change the given data without notice.					