



SISSONS PAINTS (THAILAND) LTD.

บริษัท ซีสชั่นส์เพ้นท์ส (ประเทศไทย) จำกัด

ได้รับการรับรองระบบคุณภาพมาตรฐาน ISO 9001 จาก SGS (Thailand) Limited.



91/2 หมู่ 3 ถนนสุวินทวงศ์ มีนบุรี กรุงเทพฯ 10510 โทร +66 (0) 2517 1146, 2918 6760 โทรสาร +66 (0) 2517 2137

SISCOPEOF SLURRY 1

CEMENTITIOUS WATERPROOFING MEMBRANE

PRODUCT DESCRIPTION	A 2-components cementitious waterproofing membrane. The components consisting of acrylic copolymer in Part A and premixed cement powder in Part B.	
SPECIFIC PROPERTIES	100% waterproof both positive and negative side Excellent adhesion to concrete substrate Flexible waterproof membrane Applied on damp concrete surface Supplied ready to use Can be applied by brush and trowel	
PHYSICAL DATA	Colour	Dark Grey
	Specific gravity	1.5±0.5
	Consistency	Trowellable
	Theoretical Coverage	applied at least 1.7 kg/m ²
	Mixing Ratio (A:B)	1:4
APPLICATION DATA	Application method	Brush, Trowel
	Temperature minimum	5 °C
	Humidity Maximum	85% R.H.
	Priming	Not required, <i>Saturate concrete substrate with water before application.</i>
	Mixing	Pour Part A in a clean container, keeping the mixer running, add the part B slowly. Mix for at least 3 minutes by slow-speed mixer to get a lump-free homogenous mix.
	Over coating interval	2-3 hours
	Fully cured	7 days
	Recommended thickness	minimum 1 mm
ADDITIONAL INFORMATION	Surface preparation	Surface should be sound, dry, clean, free from dust, laitance, oil, grease or any contaminations. Fill holes, grooves and cracks with cement mortar to achieve a smooth and level surface.
	Cleaning Solvent	Water
	Packaging	25 kg/set
	Storage	Store in a cool dry place, protect from direct sunlight
SAFETY PRECAUTIONS	Always wear the appropriate safety goggles and gloves during the handling. Properly dispose all used containers and excess material in accordance with the local governing safety rules and regulations. Full information about health, safety and environment of this product are provided in the Materials Safety Data Sheet	
DISCLAIMER	The information in this data sheet is given to the best of our knowledge based on laboratory testing and practical experience. However, as the product is often used under conditions beyond our control, we cannot guarantee anything but the quality of the product itself. We reserve the right to change the given data without notice.	