



SISSONS PAINTS (THAILAND) LTD.

บริษัท ซีสชั่นส์เพ้นท์ส (ประเทศไทย) จำกัด

ได้รับการรับรองระบบคุณภาพมาตรฐาน ISO 9001 จาก SGS (Thailand) Limited.



91/2 หมู่ 3 ถนนสุวินทวงศ์ มีนบุรี กรุงเทพฯ 10510 โทร +66 (0) 2517 1146, 2918 6760 โทรสาร +66 (0) 2517 2137

SISSONS ROAD LINE #222

(Cold Plastic Road Marking Paint)

PRODUCT DESCRIPTION	A two component Road marking Paint. It is designed for traffic marking applications. Formulas contain coarse aggregates for excellent slip resistance properties. Due to special selection of resin, Sissons Road Line #222 can be used in a long period of time because of its outstanding weathering resistance.	
SPECIFIC PROPERTIES	Two components which contain color in Part A and catalyst in Part B Excellent adhesion to asphalt and concrete surfaces High abrasion resistance Excellent Chemical resistance Excellent Weather resistance Slip resistance Easy to use, can be worked with trowel and roller	
PHYSICAL DATA	Solids Dry Film Thickness Wet Film Thickness Flash Point Theoretical Coverage Colours Glossiness Reflectivity Drying Time Viscosity Specific Gravity	98 % (by weight) 1000-3000 micron 1000-3000 micron > 11 °C 2.0 kg/m ² /mm Standard color (White, Yellow, Red, Black, Green, Blue) Matt Available glass beads for on-site mixing Surface Dry : 10-15 minutes Hard Dry : 1 hour (Max.) >140 KU @ 25 °C Stormer Viscometer 1.60-2.0
APPLICATION DATA	Application method Temperature Humidity Maximum Mixing Ratio Thinner/ Cleaner	Trowel, squeegee and roller 5 °C to 45 °C 85% R.H. 100 Base : 1 Hardener (by weight) Thinner No.36
ADDITIONAL INFORMATION	Cleaning Solvent Packaging	Thinner No.36 Two packs product Part A + Part B : 5.05 kg and 20.20 kg
SAFETY PRECAUTIONS	Ensure that there is adequate ventilation in the area where the product is being applied. Do not breath vapour or spray. Wear appropriate PPE. In case of touch skin, wash skin thoroughly with soap and water. In case of accidental eyes splashes, flush eyes with warm water and immediately obtain medical advice.	
DISCLAIMER	The information in this data sheet is given to the best of our knowledge based on laboratory testing and practical experience. However, as the product is often used under conditions beyond our control, we cannot guarantee anything but the quality of the product itself. We reserve the right to change the given data without notice.	